



Technical Data Sheet

Harkness Industries MP 600

Polyurethane Composition

MP 600 is a high performance polyester based urethane. This polyurethane is formulated to give an excellent balance of properties for a wide variety of applications including springs, scraper blades, die cutting pads, bumpers, bushings, wheels, tires, and many more.

Physical Properties

Shore A Hardness	60 +/- 5
100% Modulus, psi (Mpa)	250 (1.7)
300% Modulus, psi (Mpa)	600 (4.1)
Tensile, psi (Mpa)	4500 (31.1)
Elongation, %	500%
Tear Strength, Die C (ASTM D-624) pli, (kN/m)	200 (34.8)
Compression Set %	10
22 hours @ 158°F (70°C), Method B	
Tabor Abrasion, H-18 100 gm Load	
Average Loss / 1000 cycles, grams	0.030
Bell Brittle Point, °F (°C)	- 70 (-57)
Specific Gravity	1.26



50 Grandview Court
Cheshire, CT. 06410

Phone: 203-272-3219
Fax: 203-272-0428
Website: www.harknessindustries.com

