



Technical Data Sheet

Harkness Industries MP 750

Polyurethane Composition

MP 750 is a high performance polyester based urethane. This polyurethane is formulated to give an excellent balance of properties for a wide variety of applications including springs, scraper blades, die cutting pads, bumpers, chute liners, wheels, tires, and many more.

Physical Properties

Shore A Hardness	75 +/- 5
100% Modulus, psi (Mpa)	350 (2.4)
300% Modulus, psi (Mpa)	1000 (6.8)
Tensile, psi (Mpa)	5500 (37.6)
Elongation, %	500%
Tear Strength, Split (ASTM D-470) pli, (kN/m)	66 (11.4)
Tear Strength, Die C (ASTM D-624) pli, (kN/m)	250 (43.6)
Bashore Rebound, %	
Compression Set %	15
22 hours @ 158°F (70°C), Method B	
Bell Brittle Point, °F (°C)	- 70 (-57)
Tabor Abrasion, H-18 100 gm Load	
Average Loss / 1000 cycles, grams	0.040
Specific Gravity	1.26

